

Project:

Order No: Premio EPS100 Compression test


Part No: P100/1/_2018_07_25(1)

Customer: Grip-Engineering

Tester: Thümler GmbH-Z5

Method: Compression test

Execution date: 2018. 07. 25. 16:33:29

Chart:**Results:**

Nom	Stress [kPa] ,max.	Displacement [mm] ,max.
P100/1/_2018_07_25(1)	105,44	9,99
P100/1/_2018_07_25(2)	103,12	9,99
P100/3/_2018_07_25(3)	105,70	9,99
P100/4/_2018_07_25(4)	104,14	10,00
P100/5/_2018_07_25(5)	93,12	10,00
P100/5/_2018_07_25(6)	102,52	9,99
Max.	105,70	10,00
Min.	93,12	9,99
Mean	102,34	9,99