

Project:

Order No: Premio EPS80 Compression test

Part No: P80/2018_09_20(1)


Customer: Premio Hungária

Tester: Thümler GmbH-Z5

Method: MSZ EN 826

Execution date: 2018. 09. 20. 14:29:32

Chart:



Results:

Nom	Stress [kPa] ,max.	Displacement [mm] ,max.
P80/2018_09_20 (1)	83,45	10,00
P80/2018_09_20 (2)	82,89	10,00
P80/2018_09_20 (4)	83,37	9,99
P80/2018_09_20 (5)	78,55	9,99
P80/2018_09_20 (8)	80,61	9,99
Max.	83,45	10,00
Min.	78,55	9,99
Mean	81,78	9,99