

Project:

Order No: Premio EPS80 Carbon Compression test

Tester: Thümler GmbH-Z5


Part No: P80/2018_09_24(1)

Method: MSZ EN 826

Customer: Premio Hungária

Execution date: 2018. 09. 24. 16:22:42

Chart:



Results:

Nom	Stress [kPa] ,max.	Displacement [mm] ,max.
P80/2018_09_24 (1)	84,82	9,99
P80/2018_09_24 (2)	82,44	9,99
P80/2018_09_24 (3)	80,17	10,00
P80/2018_09_24 (6)	85,60	9,99
Max.	85,60	10,00
Min.	80,17	9,99
Mean	83,26	9,99