

Project:

Order No: Premio EPS100 Compression test

Part No: P100/2019_01_11(1)


Customer: Premio Hungária

Tester: Thümler GmbH-Z5

Method: MSZ EN 826

Execution date: 2019. 01. 11. 14:15:37

Chart:



Results:

Nom	Stress [kPa] ,max.	Displacement [mm] ,max.
P100/2019_01_11(1)	108,13	9,99
P100/2019_01_11(2)	105,75	10,00
P100/2019_01_11(3)	102,78	9,99
P100/2019_01_11(4)	107,46	10,00
Max.	108,13	10,00
Min.	102,78	9,99
Mean	106,03	9,99