

Project:

Order No: Premio EPS80 Compression test

Part No: P80/2019_01_31(1)


Customer: Premio Hungária

Tester: Thümler GmbH-Z5

Method: MSZ EN 826

Execution date: 2019. 01. 31. 13:25:33

Chart:



Results:

Nom	Stress [kPa] ,max.	Displacement [mm] ,max.
P80/2019_01_31 (1)	80,92	9,99
P80/2019_01_31 (2)	79,65	9,99
P80/2019_01_31 (3)	80,68	9,99
P80/2019_01_31 (4)	80,77	9,99
Max.	80,92	9,99
Min.	79,65	9,99
Mean	80,51	9,99