

Project:

Order No: Premio EPS80 Compression

Part No: P80/1/2018_08_02


Customer: Premio Hungária

Tester: Thümler GmbH-Z5

Method: Compression test

Execution date: 2018. 08. 02. 8:53:20

Chart:



Results:

Nom	Stress [kPa] ,max.	Displacement [mm] ,max.
P80/1/2018_08_02	80,26	9,99
P80/2/2018_08_02	82,00	9,99
P80/3/2018_08_02	79,34	10,00
P80/4/2018_08_02	81,65	9,99
P80/5/2018_08_02 Compression Test(5)	82,03	9,99
Max.	82,03	10,00
Min.	79,34	9,99
Mean	81,05	9,99