

Project:

Order No: Premio EPS100 Compression test

Part No: P100/2019_07_23


Customer: Premio Hungária

Tester: Thümler GmbH-Z5

Method: MSZ EN 826

Execution date: 2019. 07. 23. 15:40:23

Chart:



Results:

Nom	Stress [kPa] ,max.	Displacement [mm] ,max.
P100_2019_07_23	102,03	10,00
P100_2019_07_23	101,62	9,99
P100_2019_07_23	102,85	9,99
P100_2019_07_23	104,42	9,99
Max.	104,42	10,00
Min.	101,62	9,99
Mean	102,73	9,99