

Project:

Order No: Premio EPS80 Compression test

Part No: P80/2019_09_27(1)


Customer: Premio Hungária

Tester: Thümler GmbH-Z5

Method: MSZ EN 826

Execution date: 2019. 09. 27. 14:41:52

Chart:



Results:

Nom	Stress [kPa] ,max.	Displacement [mm] ,max.
P80/2019_09_27 (1)	80,82	9,99
P80/2019_09_27 (3)	80,98	9,99
P80/2019_09_27 (5)	85,05	9,99
P80/2019_09_27 (6)	81,20	10,00
Max.	85,05	10,00
Min.	80,82	9,99
Mean	82,01	9,99